



化學成份、硬度及導電率

品名	化學成份%	硬度(HBR)	導電率%(20°C)
鉻銅 YCC	Bu:99 Cr:0.5~1	72min	75min
鉻鋇銅 YCCZ	Cu:98.5 Cr:0.5~1 Zr:0.2	75min	75min
鉍銅 YCBC	Be:1.6~2.0 Co:0.6 Cu:Re	34min	22min
鎢銅 YCU-W	Cu:30 W:70	80min	28min



規格尺寸及特性用途



品名 Description	規格尺寸：(Specification)	
鉻銅棒 (C.C.Bar)	外 徑 O.D. 2mm~200mm	長 Length 1000mm
鉻銅板 (C.C.Plates)	厚 度 thickness 2mm~150mm	寬 Widthess 50mm~300mm
鉻銅盤 (C.C.Disks)	厚 度 thickness 5t~100t	圓 徑 50 φ ~550 φ
用途：放電加工、點焊用、電機部品、輪焊、汽車工業		

